

Metric

Typical Product Codes Supplied	P250 to P500US		
Nominal Thickness	0.25mm to 0.50mm		
Binder	Urea Formaldehyde		
	P450US	Made to order Minimum	Made to order Maximum
Glass Type	C-glass	-	-
Fibre Diameter	12-13 μ	-	-
Weight	48-51 g/m ²	-	-
Nominal Thickness	0.50 mm	0.2 mm	1.1 mm
Binder Type	Modified UF	-	-
Binder Content	15-17%	-	-
Reinforcement	25 Tex Sliver	-	-
Minimum Tensile Strength Longitudinal	125 N/50mm	-	-
Lateral	40 N/50 mm	-	-
Roll Width	-	75 mm	2.0 m
Roll Length	-	50 m	350 m

Imperial

Typical Product Codes Supplied	P250 to P500US		
Nominal Thickness	0.010 in. to 0.020 in.		
Binder	Urea Formaldehyde		
	P450US	Made to order Minimum	Made to order Maximum
Glass Type	C-glass	-	-
Fibre Diameter	0.0005 in.	-	-
Weight	161 oz/ft. ²	-	-
Nominal Thickness	0.020 in.	0.008 in.	0.043 in.
Binder Type	Modified UF	-	-
Binder Content	15-17%	-	-
Reinforcement	25 Tex Sliver	-	-
Minimum Tensile Strength Longitudinal	14 lbs/in.	-	-
Lateral	4.5 lbs/in.	-	-
Roll Width	-	3 in.	79 in.
Roll Length	-	160 ft.	1150 ft.